



## Examid® PA66 CF30Y

carbon fiber reinforced polyamide 66

Technical DataSheet | Supplied by Material Wizard

Examid® PA66 CF30Y by Material Wizard is a high-performance polyamide 66 compound reinforced with 30% carbon fiber, engineered for demanding structural and load-bearing applications where stiffness, strength, and thermal stability are critical.

The material provides excellent tensile and flexural strength, combined with a high modulus and low deformation under mechanical load, making it suitable for components exposed to continuous stress and elevated service temperatures.

This grade ensures robust and predictable performance across industrial, automotive, and technical applications where metal replacement, structural rigidity, and long-term stability are required.


|                                      |  |   |
|--------------------------------------|--|---|
| <b>Product Type</b>                  | PA (Polyamide, Nylon) >  | PA 66 CF30 (carbon fiber filled)                  |
| <b>Applications/ Recommended for</b> | Injection Molding >  | High-stress Mechanical Parts<br>Metal Replacement |
| <b>Key Features</b>                  | Excellent tensile and flexural properties<br>High dimensional accuracy<br>Elevated thermal resistance under sustained load (HDT)<br>Reduced anisotropy and improved dimensional stability<br>Controlled melt flow behavior |   |

## Examid® PA66 CF30Y Typical Properties

| Physical                             | Value & Unit           | Test Condition     | Test Method |
|--------------------------------------|------------------------|--------------------|-------------|
| Density                              | 1.30 g/cm <sup>3</sup> | At 23°C            | ISO 1183    |
| Carbon fiber content                 | 30%                    |                    | internal    |
| Melt Volume Flow Rate (MVR)          | 12 g/10 min            | At 275°C, 2.16kg   | ISO 1133    |
| Linear Mold Shrinkage, Flow          | 0.4 %                  |                    | internal    |
| Temp. of deflection under load (HDT) | 230°C                  | 1.8 MPa            | ISO 75-2/B  |
| Mechanical                           | Value & Unit           | Test Condition     | Test Method |
| Flexural Modulus                     | 18200 MPa              | At 23°C, 2 mm/min  | ISO 178     |
| Flexural Strength                    | 290 MPa                | At 23°C, 2 mm/min  | ISO 178     |
| Impact Strength, Notched Charpy      | 7 kJ/m <sup>2</sup>    | At 23°C            | ISO 179/1eU |
| Tensile Strength                     | 280 MPa                | At 23°C, 10 mm/min | ISO 527-2   |
| Tensile Strain at Break              | 3%                     | At 23°C, 10 mm/min | ISO 527-2   |

# Processing Recommendations

## Processing Conditions > Injection Molding:



|    | Zone1 | Zone2 | Zone3 | Zone4 | Adaptor | Die1 | Die2 |
|----|-------|-------|-------|-------|---------|------|------|
| °C | 270   | 275   | 280   | 285   | 290     | 300  | 310  |

## Processing Recommendations > Drying:

Our materials are supplied pre-dried in moisture-guarded bags. However, dry materials will rapidly absorb moisture when exposed to the atmosphere. For recyclable products, it must be dried before processing. It is recommended to dry the material at 120 °C for 4 hours in a circulating air or dehumidified air dryer. The moisture content must be lower than 0.2% before and during processing.

## Disclaimer

### Standard Disclaimer

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and are subject to change without notice. It is expressly understood and agreed that you assume and hereby release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. Typical Properties data is provided as general information only. Property values are approximate and are not part of the product specifications.

## Contact Information

**Email:** [vyekimov@gmail.com](mailto:vyekimov@gmail.com)

**Website:** [materialwizard.com.ua](http://materialwizard.com.ua)

**Marketplace:** [polyamide.prom.ua](http://polyamide.prom.ua)

**Phone:** + 38 050 323 23 21

